



Grayson
fixings & fasteners

TECHNICAL DATA & COMPLIANCE

LOW DENSITY JOINTFILLERS

All materials are fully compliant with the following: D.O.T specification for highway works Part 3 clause 1015 BS5268 Part 3: 1985 Section 20.4 for movement joints in brickwork.

		UNIT		TEXELL 2	
Compressive strength	10%	KPA		24	
	25%	KPA		43	
	50%	KPA		100	
Compression set 24 hour	25% 23°C	%		6	
Tensile strength		KPA		250	
Elongation at break		%		85	
Density		kg/m³		33	
Operating temperature		°C		-40+90	
Water absorption	7 day immersion	Vol.%		0.6	
				Crosslinked	
Sheet size				2m X 1m	
				2.25m X 1.5m	